






Základní technické údaje:

Druh:	<u>FALIDA</u>		
Určení:	potahová tkanina		ČSN EN ISO
Materiálové složení:		56 % PE, 44 % VI	
Šíře:		150 cm	
Hmotnost:		540 g/m	
Dostava osnovy / útku:	osnova: útek:	70 nití / cm 30 nití / cm	
Pevnost v tahu:	osnova: útek:	2 154 N 1 398 N	13934-1 13934-1
Pevnost v dotržení:	osnova-přetrh útků: útek-přetrh osnovy:	220 N 123 N	13937-3 13937-3
Odolnost v oděru:	Martindale:	8 125 otáček	12947-2
Odolnost proti žmolkování:	stupeň:	5	12945-2
Posuv nití ve švu:	posuv osnovních nití: posuv útkových nití:	4 mm 2 mm	13936-2 13936-2
Stálobarevnost:	na světle: při šamponování: v suchém otěru: v mokřém otěru:	4-5 4-5 4-5 4-5	105-B02 80 0168 105-X12 105-X12
Způsob ošetřování:		šamponování 	
Změna rozměrů po praní:	osnova: útek:	-0,5% -2,0%	
Změna rozměrů po chemickém čištění:	osnova: útek:	-2,3% -0,7%	
Kategorie:	C – běžné použití v domácnosti		14 465
Možné provedení:	nešpinivé, nehořlavé, zatemňující zátěr (jen u větších množství)		



Vzory a jejich opakování:



Všechny vzory jsou chráněny autorskými právy.



KOLOVRAT, ČM s. r. o.
Glamorous Jacquard Fabrics
CZ-391 55 Chýnov

Article:	<u>FALIDA</u>		
Applications:	upholstery fabric		
Composition:		56 % PE, 44 % VI	
Width:		150 cm	
Mass:		540 g/m	
Yarn density:	warp:	70 threads/cm	
	weft:	30 threads/cm	
Tensile strength:	warp:	2 154 N	
	weft:	1 398 N	
Tear strength:	warp:	220 N	
	weft:	123 N	
Abrasion thread breakage:	Martindale:	8 125 cycles	
Tear fastness:	degree:	5	
Seam slippage:	warp direction:	4 mm	
	weft direction:	2 mm	
Colour fastness:	to light:	4-5	
	to shampooing:	4-5	
	to dry rubbing:	4-5	
	to wet rubbing:	4-5	
Maintenance:		shampooing 	
Shrinkage after washing:	warp:	-0,5%	
	weft:	-2,0%	
Shrinkage after chemical cleaning:	warp:	-2,3%	
	weft:	-0,7%	
Modifications:	flame retardant, dirty repellent, blackout (larger quantities only)		
Designs and repeats:	2168	→ 5 cm	↓ 25 cm
	2169	→ 19 cm	↓ 40 cm

All designs are protected by copyright.

TLF: +420 381 297 011
FAX: +420 381 297 029
E-Mail: info@kolovrat.cz
http:// www.kolovrat.cz

Identification No.: 47252561
VAT No.: CZ47252561
Registration No.: České Budějovice, C 2213