




KOLOVRAT, ČM s. r. o.
stylové dekorační látky
391 55 Chýnov

Základní technické údaje:

Druh:	<u>PENELOPA</u>		
Určení:	dekorační a potahová tkanina	 	ČSN EN ISO
Materiálové složení:		100 % PE	
Šíře:		150 cm	
Hmotnost:		325 g/m	
Dostava osnovy / útku:	osnova:	70 nití / cm	
	útek:	26 nití / cm	
Pevnost v tahu:	osnova:	2009 N	13934-1
	útek:	1311 N	13934-1
Odolnost v oděru:	Martindale:	33 000 otáček	12947-2
Posuv nití ve švu:	posuv osnovních nití:	2,0 mm	80 0842
	posuv útkových nití:	0,5 mm	80 0842
Stálobarevnost:	na světle:	4	105-B02
	při šamponování:	5	80 0168
	v suchém otěru:	4-5	105-X12
	v praní:	5	105-C06
	v chemickém čištění:	5	105-D01
	v mokřém otěru:	4-5	
Způsob ošetřování:		praní při 40 °C, chemické čištění, šamponování	
			
Změna rozměrů po praní:	osnova:	-0,5 %	25077
	útek:	0,0 %	25077
Změna rozměrů po chemickém čištění:	osnova:	-0,5 %	3175-1,2
	útek:	0,0 %	3175-1,2
Skupina namáhání potahu:	3 – běžné použití v domácnosti		549-80-96
Úprava:	předsrážení		
Možné provedení:	nešpinivé, nehořlavé, zatemňující zátěr (jen u větších množství)		
Vzory a jejich opakování:	2098 → 6 cm ↓ 6 cm		
	2102 → 38 cm ↓ 19 cm		
	2122 bez vzoru		








Všechny vzory jsou chráněny autorskými právy.

TLF 381 297 011
FAX 381 297 029
E-Mail: info@kolovrat.cz
http:// www.kolovrat.cz

IČO: 47252561
DIČ: CZ47252561
OR: Krajský soud České Budějovice, C 2213



KOLOVRAT, ČM s. r. o.
Glamorous Jacquard Fabrics
CZ-391 55 Chýnov

Article:	<u>PENELOPA</u>	
Applications:	decorative and upholstery fabric	 
Composition:		100 % PE
Width:		150 cm
Mass:		325 g/m
Yarn density:	warp:	70 threads/cm
	weft:	26 threads/cm
Tensile strength:	warp:	2009 N
	weft:	1311 N
Abrasion thread breakage:	Martindale:	33 000 cycles
Seam slippage:	warp direction:	2,0 mm
	weft direction:	0,5 mm
Colour fastness:	to light:	4
	to shampooing:	5
	to dry rubbing:	4-5
	to washing:	5
	to chemical cleaning:	5
	to wet rubbing:	4-5
Maintenance:		shampooing     
Shrinkage after washing:	warp:	-0,5 %
	weft:	0,0 %
Shrinkage after chemical cleaning:	warp:	-0,5 %
	weft:	0,0 %
Finishing:	preshrinking	
Modifications:	flame retardant, dirty repellent, blackout (larger quantities only)	
Designs and repeats:	2098	→ 6 cm ↓ 6 cm
	2102	→ 38 cm ↓ 19 cm
	2122	bez vzoru

All designs are protected by copyright.

TLF: +420 381 297 011
FAX: +420 381 297 029
E-Mail: info@kolovrat.cz
http:// www.kolovrat.cz

Identification No.: 47252561
VAT No.: CZ47252561
Registration No.: České Budějovice, C 2213