





**KOLOVRAT, ČM s. r. o.**  
stylové dekorační látky  
391 55 Chýnov

**Základní technické údaje:**

<b>Druh:</b>	<b><u>PETRUSCA</u></b>		
<b>Určení:</b>	dekorační a potahová tkanina		ČSN EN ISO
<b>Materiálové složení:</b>	85 % CO, 15% PE		
<b>Šíře:</b>	150 cm		
<b>Hmotnost:</b>	670 g/m		
<b>Dostava osnovy / útku:</b>	osnova:	70 nití / cm	
	útek:	52 nití / cm	
<b>Pevnost v tahu:</b>	osnova:	1112 N	13934-1
	útek:	1100 N	13934-1
<b>Odolnost v oděru:</b>	Martindale:	18 000 otáček	12947-2
<b>Posuv nití ve švu:</b>	posuv osnovních nití:	1,2 mm	80 0842
	posuv útkových nití:	1,2 mm	80 0842
<b>Stálobarevnost:</b>	na světle:	6	105-B02
	v praní:	4-5	105-C06
	v suchém otěru:	5	105-X12
	v chemickém čištění:	4-5	105-D01
	v mokřém otěru:	4-5	
<b>Způsob ošetřování:</b>	šamponování 		
<b>Změna rozměrů po chemickém čištění:</b>	osnova:	- 2,5%	3175-1,2
	útek:	- 2,0 %	3175-1,2
<b>Změna rozměrů po praní:</b>	osnova:	- 8,0%	25077
	útek:	- 7,5 %	25077
<b>Skupina namáhání potahu:</b>	2 – nenáročné použití v domácnosti		549-80-96
<b>Možné provedení:</b>	nešpinivé, nehořlavé, zatemňující zátěr (jen u větších množství)		
<b>Vzory a jejich opakování:</b>	<b>2138</b> → 38 cm ↓ 34 cm		

Všechny vzory jsou chráněny autorskými právy.




TLF 381 297 011  
FAX 381 297 029  
E-Mail: [info@kolovrat.cz](mailto:info@kolovrat.cz)  
http:// [www.kolovrat.cz](http://www.kolovrat.cz)

IČO: 47252561  
DIČ: CZ47252561  
OR: Krajský soud České Budějovice, C 2213



**KOLOVRAT, ČM s. r. o.**  
*Glamorous Jacquard Fabrics*  
**CZ-391 55 Chýnov**

---

<b>Article:</b>	<b><u>PETRUSCA</u></b>	
<b>Applications:</b>	decorative and upholstery fabric	 
<b>Composition:</b>	85 % CO, 15% PE	
<b>Width:</b>	150 cm	
<b>Mass:</b>	670 g/m	
<b>Yarn density:</b>	warp:	70 threads/cm
	weft:	52 threads/cm
<b>Tensile strength:</b>	warp:	1112 N
	weft:	1100 N
<b>Abrasion thread breakage:</b>	Martindale:	18 000 cycles
<b>Seam slippage:</b>	warp direction:	1,2 mm
	weft direction:	1,2 mm
<b>Colour fastness:</b>	to light:	6
	to washing:	4-5
	to dry rubbing:	5
	to chemical cleaning:	4-5
	to wet rubbing:	4-5
<b>Maintenance:</b>	shampooing 	
<b>Shrinkage after chemical cleaning:</b>	warp:	- 2,5%
	weft:	- 2,0 %
<b>Shrinkage after washing:</b>	warp:	- 8,0%
	weft:	- 7,5 %
<b>Modifications:</b>	flame retardant, dirty repellent, blackout (larger quantities only)	
<b>Designs and repeats:</b>	<b>2138</b>	→ 38 cm    ↓ 34 cm

All designs are protected by copyright.

TLF: +420 381 297 011  
FAX: +420 381 297 029  
E-Mail: [info@kolovrat.cz](mailto:info@kolovrat.cz)  
http:// [www.kolovrat.cz](http://www.kolovrat.cz)

Identification No.: 47252561  
VAT No.: CZ47252561  
Registration No.: České Budějovice, C 2213