







**KOLOVRAT, ČM s. r. o.**  
stylové dekorační látky  
391 55 Chýnov

**Základní technické údaje:**

<b>Druh:</b>	<b><u>TREMEZA C</u></b>		
<b>Určení:</b>	dekorační a potahová tkanina	 	ČSN EN ISO
<b>Materiálové složení:</b>		95 % PE, 5 % AF	
<b>Šíře:</b>		150 cm	
<b>Hmotnost:</b>		350 g/m	
<b>Dostava osnovy / útku:</b>	osnova:	70 nití / cm	
	útek:	52 nití / cm	
<b>Pevnost v tahu:</b>	osnova:	1736 N	13934-1
	útek:	916 N	13934-1
<b>Odolnost v oděru:</b>	Martindale:	30 125 otáček	12947-2
<b>Posuv nití ve švu:</b>	posuv osnovních nití:	0,6 mm	80 0842
	posuv útkových nití:	1,2 mm	80 0842
<b>Stálobarevnost:</b>	na světle:	6-7	105-B02
	v suchém otěru:	4-5	105-X12
	v praní:	4-5	105-C06
	v chemickém čištění:	4-5	105-D01
<b>Způsob ošetřování:</b>		šamponování	
			
<b>Změna rozměrů po praní:</b>	osnova:	0 %	25077
	útek:	0 %	25077
<b>Změna rozměrů po chemickém čištění:</b>	osnova:	-1,5 %	3175-1,2
	útek:	+0,5 %	3175-1,2
<b>Skupina namáhání potahu:</b>	4 – náročné použití v domácnosti nebo běžné ve veřejných prostorech		549-80-96
<b>Úprava:</b>	předsrážení		
<b>Možné provedení:</b>	nešpinivé, nehořlavé, zatemňující zátěr (jen u větších množství)		
<b>Vzory a jejich opakování:</b>			

**C 2120**



Všechny vzory jsou chráněny autorskými právy.




TLF 381 297 011  
FAX 381 297 029  
E-Mail: [info@kolovrat.cz](mailto:info@kolovrat.cz)  
http:// [www.kolovrat.cz](http://www.kolovrat.cz)

IČO: 47252561  
DIČ: CZ47252561  
OR: Krajský soud České Budějovice, C 2213



**KOLOVRAT, ČM s. r. o.**  
*Glamorous Jacquard Fabrics*  
**CZ-391 55 Chýnov**

---

<b>Article:</b>	<b><u>TREMEZA C</u></b>		
<b>Applications:</b>	<b>decorative and upholstery fabric</b>		
<b>Composition:</b>		95 % PE, 5 % AF	
<b>Width:</b>		150 cm	
<b>Mass:</b>		350 g/m	
<b>Yarn density:</b>	warp:	70 threads/cm	
	weft:	52 threads/cm	
<b>Tensile strength:</b>	warp:	1736 N	
	weft:	916 N	
<b>Abrasion thread breakage:</b>	Martindale:	30 125 cycles	
<b>Seam slippage:</b>	warp direction:	0,6 mm	
	weft direction:	1,2 mm	
<b>Colour fastness:</b>	to light:	6-7	
	to dry rubbing:	4-5	
	to washing:	4-5	
	to chemical cleanig:	4-5	
<b>Maintenance:</b>		shampooing	
			
<b>Shrinkage after washing:</b>	warp:	0 %	
	weft:	0 %	
<b>Shrinkage after chemical cleaning:</b>	warp:	-1,5 %	
	weft:	+0,5 %	
<b>Finishing:</b>	preshrinking		
<b>Modifications:</b>	flame retardant, dirty repellent, blackout (larger quantities only)		
<b>Designs and repeats:</b>	<b>C 2120</b>	→ 38 cm	↓ 62 cm

All designs are protected by copyright.

TLF: +420 381 297 011  
FAX: +420 381 297 029  
E-Mail: [info@kolovrat.cz](mailto:info@kolovrat.cz)  
http:// [www.kolovrat.cz](http://www.kolovrat.cz)

Identification No.: 47252561  
VAT No.: CZ47252561  
Registration No.: České Budějovice, C 2213